



## TECHNICAL BULLETIN

### Highlights

POWERCRON 6000CX is PPG's epoxy technology known for its robust operation.

Features include:

- Wide window of operation
- Excellent corrosion resistance
  - No lead, chrome or zinc
  - Excellent performance with non-chrome sealers
  - Improved performance with zirconium pretreatment
- Reduced emissions
  - VOC less than 0.5 lb/gal
  - Non-HAP coating
- Performance advantages
  - Good protective throwpower
  - Smooth film appearance
  - Good topcoatability
- One-Component feed system
  - Improved quality and consistency
  - Reduced lab testing
  - Simplified material handling

### Technical Properties

Property	Test Method	Performance
Color	---	Black
Film Thickness	---	0.5 - 1.5 Mils
Gloss - 60 Degree	ASTM D523	65 - 85
Pencil Hardness	ASTM D3363	2H Minimum
Direct Impact	ASTM D2794	100 in-lb Minimum
Reverse Impact	ASTM D2794	60 in-lb Minimum
Crosshatch Adhesion	ASTM D3359	4B - 5B
Humidity	ASTM D1735	1000 Hours Minimum
Water Immersion	ASTM D870	250 Hours Minimum
Gravelometer	GM9508P	6 Minimum
Throwpower	GM9535P	12 - 15 inches

Cold Rolled Steel Lab Panels, Zinc Phosphate Pretreatment.  
0.6 mils Average Film Thickness, Cure 20 Minutes @ 350°F

Property	Substrate / Pretreatment	Salt Spray* 1000 Hours	20 Cycle** Scab
Corrosion Resistance	CRS/Zinc Phos/Non-Chrome	1 - 2 mm	1 - 2 mm
	CRS/Iron Phos/Non-Chrome	3 - 6 mm	3 - 8 mm

(Average Total Scribe Creep), \* Salt Spray - ASTM B117

\*\* Cycle Scab - GM9511P, Cold Rolled Steel Lab Panels

Cure 20 Minutes @ 350°F

### Commercial Uses

- Agricultural & Construction
- Automotive Parts
- Electrical Equipment
- Heavy Duty Trucks
- Underwriter Laboratory (UL)
- And many more

### Application Data

**Standard Bake:** 20 Minutes at 350°F Metal Temperature

**VOC:** 0.45 lbs. per gallon minus water (as supplied)

**HAPs:** None

**Heavy Metals:** None

**Note:** Cationic epoxy technologies are not color stable.



PPG Industries  
151 Colfax Street  
Springdale, PA 15144  
1-800-PPG-ECOAT  
www.ppgcoat.com  
ecoatinfo@ppg.com

The technical data presented in this bulletin is based upon information believed to be currently accurate. However, no guarantees of accuracy, comprehensiveness, or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in the bulletin. Contact your PPG representative for the most up-to-date information.