



## TECHNICAL BULLETIN

### Highlights

POWERCRON 210 is PPG's one-coat economical anodic acrylic technology. Its advantages include:

- The most economical electrocoat product available based on years of manufacturing improvements.
- Single coat system.
- Excellent color control and gloss stability enhanced with excellent overbake resistance.
- Low bake capabilities as low as 300°F.
- Wide film build ranges are possible.
- Replenishment systems are manufactured and shipped at high solid levels reducing inventories and shipping costs.
- UL recognized.

### Technical Properties

Property	Test Method	Performance
Color	---	Any; Excellent Overbake
Film Thickness	---	0.8 - 1.0 Mils
Gloss - 60 Degree	ASTM D523	50 - 85
Pencil Hardness	ASTM D3363	HB - H
Crosshatch Adhesion	ASTM D3359	4B - 5B
Direct Impact	ASTM D2794	100 in-lb Minimum
Reverse Impact	ASTM D2794	60 in-lb Minimum
Salt Spray	ASTM B117	48 - 96 Hours
Humidity	ASTM D1735	500 Hours Minimum
Water Soak	ASTM D870	250 Hours Minimum

Film properties based on iron phosphate pretreatment

### Commercial Uses

- Air Diffusers
- Hangers
- Metal Office Furniture
- Metal Strapping
- Range Hoods
- Switchgear
- Toolboxes
- Wire Screen

### Application Data

**Bake:** 20 minutes at 300°F (149°C) metal temperature  
**VOC:** 1.7 - 2.7 lbs per gallon minus water (as supplied)  
**HAPs:** None  
**Heavy Metals:** None



PPG Industries  
151 Colfax Street  
Springdale, PA 15144  
1-800-PPG-ECOAT  
www.ppgcoat.com  
ecoatinfo@ppg.com

The technical data presented in this bulletin is based upon information believed to be currently accurate. However, no guarantees of accuracy, comprehensiveness, or performance are given or implied. Continuous improvements in coatings technology may cause future technical data to vary from what is in the bulletin. Contact your PPG representative for the most up-to-date information.